

COLLINS COMPANY

5470 Daniels Street

Chino, CA 91710

Phone: (800) 222-4348 | Fax: (909) 548-6908

Vinyl Coated Polyester

Colors: All standard colors

Mechanical Properties	Warp		Fill	
Adhesion (5970)	7 ± 2	lbs/2 in.	7 ± 2	lbs/2 in.
Tensile Strength (5100)	220 ± 20	lbs/in.	260 ± 20	lbs/in.
Tear Strength (5134)	90 ± 20	lbs	90 ± 20	lbs

Physical Properties	
Weight	7.5 - 8.5 Oz/Yd Sq.
Base Fabric	9x12 1000 Denier Poly WI Flat
Embossing	None

Other Properties	
Fire Retardant	Various Colors ONLY - Call For Info (Test Method: MVSS302)
Heat Sealability	Yes
Shade Screen Factor	80%
Air Permeability	> 340 CFM/F Sq.
Burst Strength ASTM D 751	320 Lbs/2 Inches

Disclaimer: Collins Company assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. Collins Company disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.